

AQUAPHOBIC



DESCRIPTION

AQUAPHOBIC is a water-repellent damp-proofing agent based on oligomeric alkyalkoxysiloxanes used in an emulsifiable form. AQUAPHOBIC is diluted with clean tap water to form an opalescent micro-emulsion, which is used for facade or injection application of porous mineral building materials to repel surface water rising and/or dampness in a substrate. The AQUAPHOBIC treatment allows substrates to continue to breathe after application of the AQUAPHOBIC dilution.

APPLICATIONS

AQUAPHOBIC is used in its diluted form as a surface water repellent to treat absorbent building materials such as cement render (float), gypsum plaster, concrete, clay bricks, sand, lime bricks, concrete blocks, natural stone (for example, granite or fine sandstone) and painted surfaces. AQUAPHOBIC, when diluted, can be injected into any of the substrates mentioned above to control rising damp.

FEATURES

- AQUAPHOBIC is used by diluting with water and mixing. The resultant dilution is ready to be applied to the substrate.
- AQUAPHOBIC is readily miscible (dilutable) with water. It is only necessary to use clean tap water for dilution and hand mixing with a flat stick.
- AQUAPHOBIC is long lasting if applied correctly and diluted to the recommended dilution ratio for the substrate.

PREPARATION

All surfaces to which AQUAPHOBIC is to be applied should be free of efflorescence, bore stains, dust, tyre marks, oils (mineral or vegetable), grease, loose material (for example builder's rubble), paint or coatings of any type, mould,

bitumen, adhesives or other silicone materials. Surfaces should also be as dry as possible before application of AQUAPHOBIC.

DIRECTIONS

AQUAPHOBIC should be diluted 9 times with clean, fresh water (1 litre of AQUAPHOBIC mixed with 9 litres of water). Mix the dilution with a flat-sided stick with a strong motion for 2-3 minutes.

NOTE: Once diluted, AQUAPHOBIC should be used within 12 hours.

WALLS: Apply two coats of diluted AQUAPHOBIC at a rate of approximately 3-4m²/litre/coat to a dry wall. Apply the two coats 2 - 4 hours apart at 25°C. For highly porous substrates, 3 applications are required.

DIRECTIONS FOR A USED SHOWER

- Wear rubber gloves, have eye protection and light protective clothing. Have windows open and a fan on.
- Clean the grout and tiles with a cleaning product such as JIF or other scouring liquid with the aid of a brush. The grout should be made free of verdigris, mould, algae, fungi, soap and scum. Dry off the grout with a dry rag.
- Dilute 100ml of AQUAPHOBIC with 400ml of water and brush the diluted AQUAPHOBIC along the grout lines and tiles, focusing on grout lines. There will be overruns onto the tiles of the AQUAPHOBIC dilution. As the application progresses, use a water dampened clean rag, rung out, to remove excess water and wipe the runs over the tile face as proceeding. When the wet application of the AQUAPHOBIC dilution is completed, remove any excess solution from the base of the shower and the grout lines with a rung out water dampened cloth. Allow the treatment to

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL: (08) 9378 2022
FAX: (08) 9377 2575
MOB: 0418 956 860

IDENTIFICATION
PAGE 1 of 2
ISSUE: JULY 2011
REF: AQP

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.

AQUAPHOBIC



dry out for about six hours, and repeat the application again.

The next day, the shower is ready for general use after this treatment.

NOTE: In most cases, one application of AQUAPHOBIC dilution is sufficient. It depends on the quality and amount of the grout in the joint. Deteriorated grout needs two applications

NOTE: The wisest precaution is to regrout and treat the new grout with AQUAPHOBIC as directed above. One treatment is sufficient in this case.

NOTE: The treatment may be slightly darken lightly coloured grouts. Test before use if this is of concern.

NOTE : It is recommended a small test area of grout and tiles are treated beforehand to check effectiveness and also to familiarise yourself with the system.

HANDLING

It is recommended to wear protective goggles, gloves and clothing when using AQUAPHOBIC. Shrubs, plants and any painted substrates or glass near the area being treated should be covered to prevent them from any contact that may inadvertently occur. AQUAPHOBIC reacts with glass causing a permanent stain after setting.

CAUTION

Keep AQUAPHOBIC away from glass as it will damage and deface plate glass because it is a silicate material.

AQUAPHOBIC is not suitable for open coarse textured substrates like Western Australian limestone.

AQUAPHOBIC when diluted should be used within 12 hours.

Do not apply AQUAPHOBIC to substrates that will encounter rain or inclement weather with 48-72 hours.

PACK SIZES

AQUAPHOBIC is sold in packs of 100mL and 1, 5 and 20 litres.

CLEAN UP

Clean up with water when AQUAPHOBIC is wet. When the AQUAPHOBIC has dried, use mineral turpentine in its initial stage.

STORAGE

Store AQUAPHOBIC in sealed containers under cover in a cool area away from foodstuffs.

TRANSPORT

FLAMMABLE LIQUID n.o.s. : CLASS 3.2 :
SUBCLASS NIL : U. N. No. 1993 : Packaging
Group III : HAZCHEM 2[S]. IEPG. No. 14.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 2 of 2
ISSUE: JULY 2011
REF: AQP/B

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.