

ASBESTOS PRIMER



DESCRIPTION

ASBESTOS PRIMER is based on a micro-particle, hard acrylic emulsion incorporating high loadings of fungicides and algicides. ASBESTOS PRIMER forms a hard, penetrative film which acts as a binder and sealer. ASBESTOS PRIMER dries quickly to form a clear film.

USE

The recommended asbestos encapsulation process requires ASBESTOS PRIMER followed by ASBESTOBOND which has a coloured top coating of either TUFSEAL or FLEXITEX. The combination of the products as listed above forms a membrane over the mould covered asbestos roof giving it a new, clean and enhanced appearance. Some asbestos roofs are very badly affected by mould growth. Mould inhibitor may also be requested for extra protection before the encapsulation coating system is applied. In both cases, FUNGATROL solution can be applied before applying ASBESTOS PRIMER.

DIRECTIONS

Wear overalls, safety boots, impervious gloves, appropriate breathing mask and eye protection. Dispose of these items after use at a registered disposal site for asbestos materials.

Any preparation or repair work must be done without freeing any asbestos fibres and making them airborne. When inhaled, asbestos fibres are very dangerous to human health and decrease longevity.

Do not high-pressure water clean or scrub the asbestos (whether painted or unpainted). Gently cut off any large growths of mould level to the surround of the substrate. Remove any loose material that peels off easily. Put any removed

material in a sealed plastic bag and dispose of it at a registered asbestos disposal site.

Repair any cracks or flashings with FIBRETAK/fibreglass mat (225g/m²).

Allow any repair products and asbestos substrate to dry out so the total substrate is suitable to accept ASBESTOS PRIMER.

APPLICATIONS

FUNGATROL TREATMENT: If this treatment is decided on, spray FUNGATROL onto the substrate at a minimum rate of 3-4m²/litre. Allow the substrate to dry. Clean out the spray unit and lines with water after using FUNGATROL.

Follow with ASBESTOS PRIMER; apply as supplied by airless spray. Application rate is dependent on the suction and state of the substrate as a whole. Spray a good coat of ASBESTOS PRIMER onto the edges of the sheets, making sure they are well sealed. Follow by sealing the fixing screws and 100ml on either side of the edges of the sheets. Finish with an even seal coating of ASBESTOS PRIMER over the remainder of the roof. Total coverage is in the region of 4m²/litre of ASBESTOS PRIMER.

When the ASBESTOS PRIMER is dry, spray on ASBESTOBOND with an airless spray at a rate of 4m²/litre. Follow by spraying two coats of either the TUFSEAL or FLEXITEX.

NOTE: For corrugated asbestos, add an extra 25-30% to the actual area of roof (in square metres) because of the additional area associated with the profile of the corrugation.

NOTE: Coverage of the various coatings will vary depending on the suction and state of the asbestos

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 1 of 2
ISSUE: JULY 2011
REF: ASPR

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)
This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.

ASBESTOS PRIMER



substrate. Do not apply the coatings outside the highest limit mentioned for coverage of a product.

CLEAN UP

All products mentioned are waterborne and can be removed with water while wet. As a dry film, use MARCMOVE or WIZSTRIP.

STORAGE

Store all products under cover, in a cool area, away from foodstuffs, with lids on when not in use.

SAFETY

Asbestos fibres are deadly. Make sure there are no fibres dislodged while carrying out the preparation and application. Wash all clothing before removing it from the body and dispose of it at a registered disposal site.

PACK SIZES

ASBESTOS PRIMER is sold in packs of 20, 200 and 1000 litres.

TRANSPORT

ASBESTOS PRIMER is not a hazardous good as defined by WorkSafe Australia.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 2 of 2
ISSUE: JULY 2011
REF: ASPR

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.