

BRYLCOTE



DESCRIPTION

BRYLCOTE is a waterborne acrylic emulsion polymer which is extremely hard, resembling solvent-borne acrylics or styrene acrylics. It is designed to be an industrial grade coating with exceptional adhesion, wear and chemical resistance.

APPLICATIONS

BRYLCOTE is used as a clear (internal) or coloured (external) sealer.

BRYLCOTE is used as a pre-sealer for high-build sealers and coatings.

BRYLCOTE is suitable for sealing a variety of concrete substrates including old concrete floors that have been cleaned and primed, but retain some embedded stains of dirt and oil.

BRYLCOTE is a suitable top sealer on new concrete floors.

BRYLCOTE can be used as a sealer on internal ceramic substrates e.g. terracotta tiles, slate.

BRYLCOTE is a suitable top sealer for FLEXI-DECK.

FEATURES

- BRYLCOTE is waterbased.
- BRYLCOTE is trafficable and easily maintained depending on the degree, type and consistency of use applied to the sealer.
- BRYLCOTE has the following properties for two coats at 10m²/litre:
- Drying time: 45-60 minutes/coat at 20°C with a good air flow.
- Adhesion: Excellent.
- Flow and spreading: Very good when applied either with a brush, soft haired broom or spray.
- Water resistance: BRYLCOTE is resistant to water contact.
- Fair to good resistance to very dilute acids and alkalis.

- Resistance to oil and detergent: excellent.
- Tyre marking, scuff and abrasion resistance: excellent

PREPARATION

Clean the surface such that it is a sound surface which is free of dust, oil, laitence, rust, mould, algae, fungi, coatings, paints, bitumens and curing compounds.

Concrete that have had previous coatings applied to them should be ground off to remove coatings. Water-blasting should follow to remove all dusts and loose material. Allow to dry before proceeding.

CONCRETE: Apply one coat PLICRETE as a primer at a rate of 4-5m²/litre. Allow to dry for at least 24 hours @25°C and 50% humidity.

Apply two coats if concrete is subject to rising moisture or is highly porous. Refer to PLICRETE pds for multi coat applications.

APPLICATION RATES

SEAL COAT ON VINYL FLOORING: Apply two coats of BRYLCOTE at 12-14m²/litre per coat. Apply with a TEE BAR PAD applicator.

SEAL COAT ON CERAMIC TILES: Apply two coats of BRYLCOTE at 8-10m²/litre per coat using only a fine brush or a soft haired broom (see 'Application method').

TOP SEAL COAT FOR ATTA-FLEX AND PLICRETE: Apply to dry set coatings, two coats at 10m²/litre per coat.

BARE CONCRETE: Apply 2 coats of BRYLCOTE at 8-10m²/litre.

APPLICATION METHOD

It is not recommended to apply by roller as there is a tendency to create air bubbles in the coating film

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 1 of 2
ISSUE: JULY 2011
REF: BLCT

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.

BRYLCOTE



by rolling too vigorously. If rollers are used, it is highly recommended to roll slowly. BRYLCOTE should be applied by a TEE BAR PAD applicator, by brush, a soft hair house broom or by low pressure spraying. Lay the BRYLCOTE off as applying it so that a thin, bubble-free, even film is applied. Drying and recoat times will vary depending on weather conditions. The colder the temperature, the longer time between recoating. For best results, allow 24 hours between coats. Full cure in 7 days at 25°C. Pedestrian traffic after 24 hours in summer, 48 hours in winter. Vehicle traffic after 3-4 days in summer, 4-5 days in winter.

CLEAN UP

Clean up wet BRYLCOTE deposits with water and dry BRYLCOTE deposits with MARCMOVE.

STORAGE

Store BRYLCOTE in sealed containers under cover in a cool area away from foodstuffs.

PACK SIZES

BRYLCOTE is sold in packs of 20 and 200 litres.

TRANSPORT

BRYLCOTE is a waterborne product and not in the hazardous goods category. It should not be transported next to food items.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 2 of 2
ISSUE: JULY 2011
REF: BLCT

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.