

DAMP-PEL W



DESCRIPTION

DAMP-PEL W is an aqueous emulsion concentrate which is used to make mineral building materials damp-proof and water repellent.

APPLICATIONS

- Injection into building foundations at or below floor level to form a damp course.
- Making plasterboard repellent.
- Making fired clay and concrete products water repellent.

DIRECTIONS

DAMP-PEL W is supplied as a concentrate and is diluted with clean, clear water with a hardness of less than 200mg/L of CaCO₃. If the water is too hard, it will interfere with the emulsion particles. When diluting, add the DAMP-PEL W to the water with good stirring. Correctly diluted DAMP-PEL W will not separate for a substantial period, e.g 1 day.

Dilutions:

Water repellent: one(1) part DAMP-PEL W to nine(9) parts water.

Damp-proofing: one(1) part DAMP-PEL W to four(4) parts water.

DAMP-PROOF COURSES

Bore 4-6mm diameter holes into the substrate 100mm apart in a 10° slope towards the ground. Pressure inject a solution of DAMP-PEL W diluted seven to nine times with water. The dilution of DAMP-PEL will require adjusting for the porosity of the substrate. Very porous substrates may need a dilution of 5-6 times. Required coverage is 1-2 litres of dilution per metre for a single 100mm wide wall.

WATER REPELLENT: Apply two coats of DAMP-PEL W as a wet on wet application. Spread rate of dilution should be 3-4m² per litre per coat.

DAMP-PEL W should not be applied or injected in rain or inclement weather is expected within 48 hours.

Drying time for water repellency application is 4 - 6 hours at 25 degrees celcius.

HANDLING & SAFETY

DAMP-PEL W should be keep away from glass or metals.

NOTE : A white deposit may form on the substrate surface if applied in excess.

TRANSPORT

DAMP-PEL W is not classified as a dangerous or hazardous good under the guidelines of WorkSafe Australia.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 1 of 1
ISSUE: JULY 2011
REF: DMPL

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)
This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.